



## Storage & Handling

Laminated bamboo sheet and veneers should be stored in a well-ventilated area away from heat sources, flames, or sparks. It should be stored flat, and protected from water or moisture ingress.

Moisture will encourage mould or mildew growth on the surface of the bamboo sheet.

Cover to protect against discolouration from UV light.

Excessive dryness will encourage warping and splitting of the exposed raw faces.

Secure your load when transporting.

Lifting a bamboo sheet clearly from the bamboo sheet beneath in the stack, will reduce the possibility of surface damage or gouging

Adhere to Safe Work Australia National Code of Practice for Manual Handling.

## 5mm Single Ply Bamboo

5mm thick single ply bamboo is designed to be pressed (in a cold press) with cross-linked PVA (Titebond or Selleys Aquadhere product) water based, nontoxic adhesive onto a substrate of heavier gauge than 5mm, and, or a rigid material, with a surface allowing key and grip.

Used alone, the bamboo will almost never hold to a flat shape, it will react to atmospheric changes resulting in cupping, splitting or twisting. It is also quite fragile to handle; splitting easily.

Sheets despatched by LETObamboo are selected for relative straightness, and without splits.

LETObamboo will not be held liable for splitting or damage caused by the receiver.

**BAMBOO SHEET MUST BE SANDED, AND SEALED TO ALL FACES, BEFORE INSTALLATION, WHEN USED FOR JOINERY, CEILING OR WALL CLADDING.**